



CONSTRUCTION  
TECHNOLOGY LABORATORIES  
ENGINEERS & CONSTRUCTION  
TECHNOLOGY CONSULTANTS

August 10, 2007

[www.CTLGroup.com](http://www.CTLGroup.com)

Via email

Mr. Jacob Webb  
NewLook International  
1525 South Gladiola Street, Suite 8  
Salt Lake City, UT 84104  
Jacob@getnewlook.com

**Slip Index Testing of NewLook Concrete Color Stains  
CTLGroup Project No. 401399, Revision 1**

Dear Mr. Webb:

Enclosed are the test results for the concrete overlay sample you submitted. You initially identified one side of the sample as "Broom Finish" (CTL ID 1859001) and the other as "Stamped Finish" (CTL ID 1859002). At a later date, you stated that both samples were treated with **NewLook Concrete Color Stain** and revised the sample identifications as "NewLook Concrete Color Stain on Concrete Overlay with Broom Finish" (CTL ID 1859001) and "NewLook Concrete Color Stain on Concrete Overlay with Stamped Finish" (CTL ID 1859002).

The Slip Index of the each surface was determined both dry and wet in accordance with ASTM F 609-96, "Standard Test Method for Using a Horizontal Pull Slipmeter (HPS)." The static coefficient of friction for a dry surface can be determined by dividing the Slip Index by 10.

We appreciate the opportunity to serve your testing needs. If you have any questions about this matter, please feel to contact me.

Very truly yours,  
**CONSTRUCTION TECHNOLOGY LABORATORIES, INC.**  
*An AASHTO Accredited Laboratory – Aggregate, Cement and Concrete*

Cyler F. Hayes  
Senior Chemist  
Materials Testing & Analysis  
[CHayes@CTLGroup.com](mailto:CHayes@CTLGroup.com)  
847.972.3164

cc: Kathy Merlo, CTLGroup

*Main Office:* 5400 Old Orchard Road Skokie, Illinois 60077-1030 Phone: 847-965-7500 Fax: 847-965-6541

*Mid-Atlantic Office:* 9030 Red Branch Road, Suite 110 Columbia, Maryland 21045-2003 Phone: 410-997-0400 Fax: 410-997-8480

*New England Office:* 1 Washington Street, Suite 300A Dover, New Hampshire 03820 Phone: 603-516-1500 Fax: 603-516-1510

CTL Project No.: 401399  
Client: NewLook International  
Project: ASTM F 609  
Contact: Jacob Webb  
Submitter: Jacob Webb

CTL Project Mgr: C. Hayes  
Technician: P. Brindise  
Approved: M. Morrison  
Date Tested: 15-May-07  
Date Reported: 10-Aug-07

**ASTM F 609 - 96, "Standard Test Method for Using a Horizontal Pull Slipmeter (HPS)"**

**Client ID: NewLook Concrete Color Stain on Concrete Overlay with Broom Finish**  
**CTL ID: 1859001**

Test Surface Condition	Shoe Sole Material	Slip Index Reading					Test Foot Thickness (inches)
		Test Direction, degrees				Average	
		0	90	180	270		
Dry	Leather	>8	7.9	7.8	>8	>7.9	0.05
	Natural Rubber	>8	>8	>8	>8	>8	0.17
	Neolite Rubber	>8	>8	>8	>8	>8	0.09
Wet	Leather	>8	>8	>8	>8	>8	0.05
	Natural Rubber	7.8	>8	7.9	>8	>7.9	0.17
	Neolite Rubber	>8	>8	>8	>8	>8	0.09

**Client ID: NewLook Concrete Color Stain on Concrete Overlay with Stamped Finish**  
**CTL ID: 1859002**

Test Surface Condition	Shoe Sole Material	Slip Index Reading					Test Foot Thickness (inches)
		Test Direction, degrees				Average	
		0	90	180	270		
Dry	Leather	6.4	6.2	6.5	6.2	6.3	0.05
	Natural Rubber	6.5	6.3	7.3	7.1	6.8	0.17
	Neolite Rubber	7.1	6.9	7.2	7.6	7.2	0.09
Wet	Leather	>8	7.8	7.9	7.7	>7.8	0.05
	Natural Rubber	7.2	7.3	6.7	6.9	7.0	0.17
	Neolite Rubber	7.0	7.3	6.8	6.8	7.0	0.09

**This report may not be reproduced except in its entirety**